Synthesis and Promising Applications of Graphene and Related Materials

Jeet Vishwakarma^{1,2}, Anushi Sharma^{1,2}, Netrapal Singh^{1,2}, Priyanka Prabhakar^{1,2}, Sarvesh Kumar Gupta¹, Rajeev Kumar¹, Surender Kumar^{1,2}, Chetna Dhand^{1,2}, Neeraj Dwivedi^{1,2,*}

¹CSIR- Advanced Materials and Processes Research Institute, Bhopal-462026, India ² Academy of Scientific and Innovative Research (AcSIR), Ghaziabad-201002, India

*Corresponding Author: <u>neeraj.dwivedi@ampri.res.in</u> and <u>neerajdwivedi6@gmail.com</u>

Abstract: In recent years, there has been extensive research on graphene and its derivatives, driven by their remarkable physicochemical and functional properties. Various forms of graphene, such as multi-layer graphene, graphene oxide, and graphene quantum dots, have shown immense potential to revolutionize multiple technologies. This review critically examines the synthesis and applications of graphene and related materials. In the synthesis section, we explore methods ranging from top-down techniques, which involve breaking down larger structures into graphene layers, to bottom-up approaches, where graphene is built up from smaller constituents. In the application segment, we comprehensively discuss the diverse uses of graphene and its derivatives. This includes their roles in electronic applications, energy storage systems, tribological applications, healthcare technologies, water desalination processes, and mechanical applications. By exploring various applications, we aim to highlight the wide-spread applications of graphenebased materials and their composites in shaping the future of multiple technologies.

Keywords: Graphene, Electronics, Energy storage, Tribology, Healthcare

1. Introduction: Graphene, a promising multifunctional material, has vast applications from pencil lead[1] to neural computing [2]. Graphene can be rolled, bundled, and stacked into 0D (fullerene, graphene quantum dots) [3, 4], 1D (nanotube, nanoribbon), and 3D (graphite) materials. The chemical model of graphene is depicted in Figure 1. Graphene exhibits exceptional properties such as high electron mobility which is 200 times higher than that of silicon under ambient conditions, ballistic electrical conductivity of $\sim 10^3$ S/m, thermal conductivity of ~5300 W/mK, excellent mechanical properties like ultimate tensile strength (UTS) of 130 GPa and elastic modulus of ~1 TPa, very high specific surface area of 2630 m²/g, excellent optical transparency (~97.7%), and less break-over voltage of ~0.3 V [5-11].

Due to these astonishing properties graphene and graphene-related materials (GRMs) are extensively used in different applications. Researchers have used various methods to synthesize graphene to obtain desirable properties and potential applications. To expand their usage, the chemical modifications of GRMs have also been executed. Despite the fact that graphene will probably enter the market as a composite, several teams are attempting to realize the full potential of the isolated sheets.

In this review, we critically discuss the synthesis and properties of graphene and GRMs. We compiled recent literature on graphene and GRMs and discussed their potential applications in the fields of high strength systems, electronics, healthcare, sensors, tribology, water desalination, and composites.

2. Synthesis of graphene: The synthesis of single-layer graphene was tried in 1975. The researchers showed that single and multilayer graphene could be produced by thermal decomposition of carbon on Pt crystal as a substrate.



Figure 1. Chemical model of graphene-related material.



Figure 2: Graphene synthesis method

However, due to the lack of understanding about such sheets and the failure to find the potential applications of these sheets, a detailed study was not conducted at that time. Later on, in 1999, scattered efforts were reported for the synthesis of graphene. However, in 2004, Geim and Novoselov were credited for the discovery of graphene [12]. For the first time, they showed the repeatable synthesis of graphene through exfoliation. After that, several methods have been reported and some of the most important synthesis (Figure 2) methods are discussed below.

2.1 Exfoliation: In graphite, the graphene sheets are bonded together by weak van der Waals bonds. These bonds can be broken to produce graphene from graphite. In exfoliation processes, mechanical or chemical energy is used to break these weak bonds and separate individual graphene sheets.

2.1.1 Chemical exfoliation: This method uses a liquid suspension that converts graphite to graphene through the formation of an intermediate compound known as a grapheneintercalated compound. Alkali metals are used to increase the interlayer spacing between the graphite layer by reducing the van der Waals forces, as these large alkali ions are placed in between the graphitic layer of graphite dispersed solution, owing to the potential ionization difference between the graphite and alkali metal. Chemical exfoliation has the benefits of a high yield and low operating temperature, but the graphene it produces tends to reassemble into graphite, hence surfactants or immiscible liquids are required [13].

2.1.2 **Mechanical exfoliation:** One of the most effective methods for obtaining singlelayer graphene flakes on desired substrates is mechanical exfoliation. In this method the peeling of the graphitic layer is happened with the help of scotch tape, ultrasonication, electric field, or even the transfer printing technique. Geim and Novoselov used mechanical exfoliation for the development of graphene [12]. They used highly oriented pyrolytic graphite (HOPG) to create 4-5 µm deep mesas. The flakes of graphene were peeled from mesas using scotch tape. These flakes were washed with acetone several times and put onto the silicon substrate.

2.2 Thermal Chemical Vapor Deposition Techniques

(i) Thermal Decomposition of SiC

The graphene can be synthesized using the thermal decomposition of silicon carbide. In this technique, SiC is heat-treated up to temperatures ranging from 1200-1500°C in an ultra-high vacuum. This leads to the removal of Si, thus leaving behind a layer of carbon [14]. Transmission electron microscopy studies were used to confirm the graphitic nature of the carbon layer or graphene. The ultrathin epitaxial films of graphite were grown by this technique on the 6H-Sic surface. The films typically contain mono and bilayer graphene sheets [15]. The primary benefit of the thermal breakdown of SiC over other traditional methods is the direct production of graphene layers on a semiconducting or semi-insulating substrate that is readily accessible for purchase, negating the need for transfer before processing electrical devices.

(ii) Molecular Beam Deposition

This technique is successfully used for the graphene growth on a variety of substrates. For example, ethylene gas is used as a carbon source and Ni substrate is exposed to a higher temperature (200°C) in an ethylene gas environment. High-quality graphene layers can be produced by this method and are capable of forming a layer on top of another [16]. The main advantage of this method is that the graphene layers are not dependent on the cooling rate which indicates that carbon was not absorbed into the Cu and Ni substrate as in CVD processes.

iii) Chemical Vapor Deposition.

In the chemical vapor deposition (CVD) technique, one can produce graphene on the transition metal (e.g. Fe, Co, Ni, Cu) at high temperature (>1000°C) with the carbon source supplied in gas form and metals like Cu and Ni is preferred as a substrate to grow the graphene layer [17-19]. Methane and acetylene gas are generally used as a source of carbon. Along with methane, hydrogen and argon are also utilized as reaction stabilizers and to improve the homogeneity of the film [20]. Furthermore, the CVD approach can be



Figure 3. Synthesis of high-quality single-layer graphene and its characterization at CSIR-AMPRI, Bhopal.

modified enhanced, including and atmospheric pressure CVD (AP-CVD), radiofrequency PE-CVD (RFP-CVD), microwave plasma CVD (MP-CVD), ultra-high vacuum CVD (UHV-CVD), plasma-enhanced CVD (PE-CVD), low-pressure CVD (LP-CVD), inductively coupled PE-CVD (ICP-CVD), and surface-wave plasma CVD (SWPCVD). A good quality graphene layer growth was demonstrated using rapid thermal process (RTP) CVD (Figure 2). For graphene deposition, firstly, Cu foils are placed in a quartz tube and heated up to 1000°C in an H₂ atmosphere for 30 min to remove residual oxide. After annealing, the sample is cooled down to room temperature. Following the preconditioning step, the Cu foil is again heated up to 1000°C and subsequently CH4 and H2 gases are introduced for 20-30 min leading to growth of graphene. After growth the sample is cooled down to room temperature.

2.3 Chemical Methods

i) Chemical oxidation and reduction

A large amount of graphene can be produced through the oxidation of graphite by treating it with strong acidic and basic oxidants. It was first introduced by Brodie in 1859 when graphite was treated with potassium chlorate (KClO₄) and fuming nitric (HNO₃) and Later in 1898, Staudenmaier NO₂.[21] modified Brodie's method and used nitric and sulphuric acid in 1:4 in an ice bath, which is considered a safer method [22] but toxic gases are still an issue. After several modifications, Hummer developed a new method that is more common for the preparation of graphene oxide using NaNO₃, KMnO₄, and H₂SO₄. Moreover, graphene oxide (GO) is prepared from high-purity graphite powder [23]. In this

method, 3g graphite powder and 1g NaNO₃ are mixed with 100 ml sulphuric acid and stirred for several minutes. After that 12g KMnO₄ is added slowly into this solution at 20°C. Then this mixture is stirred for 4-5 hours until the solution becomes dark green. After that, 140 ml of deionized water is added to this solution and stirred for 30 minutes at 98°C. Hydrogen peroxide (40 ml) is added drop by drop for removal of KMnO4 and cooled down using an ice bath. After cooling, 10 ml of hydrochloric acid and 250 ml of deionized water are added and stirred for 1 h. The residual is washed 3-4 times with 1M hydrochloric acid and deionized water. The washed GO solution is dried using an oven at 90-100°C for 24 h to produce GO powder. The prepared GO powder is sonicated and reduced to obtain graphene. Later on, the Hummers method was modified by Tour et. al. in 2010 to eliminate the toxic gases NO_2 and N₂O₄. They replaced NaNO₃ with potassium permanganate and a mixture of reactions consisting of (9:1) H₂SO₄: H₃PO₄ for oxidation reaction [24].

Graphene can also be obtained through the reduction of the conjugate structure of GO, referred to as reduced GO (rGO). Also, the electrically insulated GO is converted to the conductive by the removal of the oxygen atom to develop a partial sp² character. Reduction of GO is done by thermally, chemically, electrochemically, or green synthesis route [25].

ii) Unzipping Carbon Nanotubes

In this technique, sulphuric acid and KMnO₄ are used for cutting multi-walled carbon nanotubes (MWCNTs) in a longitudinal direction, followed by the chemical reduction of the oxidized graphene produced through hydroxide and hydrazine ammonium monohydrate. The graphene nanoribbons are developed using this method, and the developed nanoribbons are reduced by different chemicals. These nanoribbons are conducting in nature, however, due to the presence of oxygen defects, these graphene nanoribbons display electrical properties slightly inferior to graphene [11]. The were unzipped by various MWCNTs

experimental methods such as a mixture of acid, a catalytic cutting method, electrical zipping, and H-based zipping, etc.

2.4 Other Methods.

There are several other methods to produce graphene such as arc discharge of graphite, electron beam irradiation of PMMA nanofibers, thermal fusions of polyaromatic hydrocarbons, and conversion of nanodiamonds.

In addition, different types of graphene-based materials such as graphene nanoribbons, graphene quantum dots, and graphene foam or aerogel can be fabricated. Particularly, graphene foam is a 3-dimensional honeycomb structure that possesses many interesting properties such as low density, high open porosity and high surface area, good mechanical strength, excellent electrical and thermal conductivity, and good chemical and corrosion-resistant. These extraordinary properties make graphene foam a promising candidate for many engineering applications.

3. Applications of Graphene

Graphene is a wonderful material that holds promising properties such as high electron mobility which is ~100 times or even higher than silicon that is commonly used in electronics, electrical conductivity higher than copper, high transmission (about 97.7%), high thermal conductivity even higher than 3dimensional diamond, high impermeability, and many more. These properties make graphene and graphene-related materials promising candidates for numerous applications.

High Strength: The mechanical strength of graphene can reach ~130 Giga Pascal (130 Giga Pascal = 13256310768.713 Kg/m²) which is about a few hundred times higher than steel. The hexagon lattice developed by sp^2 carbon atoms restricts in-plane deformation depicting impressive mechanical strength. So, graphene can be used as fillers in polymers and metals to exceptionally enhance their mechanical strength. Numerous studies have been performed on the mechanical properties of graphene reinforced composites and their mechanical strength is generally

analyzed through stress-strain curves obtained by tensile tests. The mechanical strength of the graphene and GRMs reinforced composites depends on filler geometry, dispersion, number of graphene layers and size, the interaction between matrix and filler, and the fabrication process. Gong et.al studied the effect of how the number of graphene layers influences the mechanical properties of polymer matrix [34].

Kim et al designed nanolayered composites with alternate layers of single-layer graphene and a layer of metal (copper or nickel) and found high mechanical strength of 1.5 GPa and 4 GPa in graphene-copper and graphenenickel structures, respectively [35]. Jeon et. al



Figure 4: Schematic representation of graphene in different applications (a) miniature ballistic tests by firing tiny silica spheres at sheets of graphene [26] (b) metal-graphene-metal (MGM) photodetectors with asymmetric metal contacts [27](c) Schematic illustration for the preparation process of epirubicin/ NGO-HA complex and the target specific delivery of the complex to cancer cell via HA receptor mediated endocytosis [28] (d) illustration of the relationship between graphitization degree and lubrication performance [29] (e) sweat sensor [30] (f) schematic depiction of the synthesis and electrochemical performance of PdPGO for supercapacitor [31] (g) Side view of an individual simulation system, composed of a piston, a membrane with a nanopore and two water boxes. The left water box is saline while the right one is fresh water[32] (h)polymer-graphene nanocomposite in aerospace [33].

investigated the effect of the size of graphene nanosheets (1 µm, 750 nm, 250 nm, and 20 nm) on the mechanical properties of polymer nanocomposites and found that effective interfacial adhesion is greater for large size graphene nanosheets due to large contact area that influences the mechanical properties [36]. However, the concentration percentage of the graphene and GRMs for both polymer and metal matrix goes through the threshold value up to which the mechanical strength increases, and after that distortion of properties occurs. In civil structures, the application of 0.05 wt. % of graphene resulted in 8%, 79%, and 9% enhancement of compressive strength, tensile strength, and Young's modulus of ordinary Portland cement, respectively [37]. The graphene reinforced shape memory polymers [38], shape memory metallic alloys [39], automobile components, and engineering components are some examples where graphene has been exploited to enhance the mechanical strength and other mechanical properties of the systems. For example, Krishnamoorthy et. al designed a siloxenegraphene heterostructure electrode-based symmetric supercapacitors that delivers a maximum power density of 15 000 W kg⁻¹ and high energy density $(55.79 \text{ Wh kg}^{-1})$ [40]. Le et al. designed alligned graphene/carbon nanotube fibers that possess high mechanical strength and excellent electrical properties [41].

Electronic Applications: Graphene displays extremely high carrier mobility that can be reached to about 10^5-10^6 cm²V⁻¹s⁻¹, which is about 2 to 3 orders of magnitude higher than commonly used semiconductors such as silicon. Thus, graphene has a bright future for electronic applications such as in the development of micro- and nano-electronics devices. It is the potential alternative to silicon technology [42] and its distinct optoelectronic characteristics make it a perfect medium for rapid photodetectors [43], optical modulators [44], plasmonic devices [45], ultrafast lasers [46] etc. A graphene-based transistor can develop faster electronic devices. GRMs,

especially nanoribbons, are appealing structures for logic microprocessors due to high current-carrying capacity, high carrier mobility, and, saturation velocity, thereby enabling high performance at a lower power supply. Moreover, semiconducting GNRs are appealing not just for logic applications but also for low power radio frequency (RF) technologies and a variety of novel devices in quantum informatics, thin-film electronics, and spintronic (such as flexible devices and sensors)[47, 48]. Importantly, in silicon-based CMOS technology, the number of transistors per processor is increased by reducing the gate However, conventional length. CMOS technology is reaching the fundamental limit. Thus, not only the graphene's extremely high carrier mobility important, but also atomic thinness can play a vital role, and together both these properties can enable the development of futuristic high-speed fieldeffect transistor (FET) technology. Indeed, graphene-based FET has shown exceptional electrical behavior [49-51]. Owing to their high mobility and conductivity, high optical transparency, and sharp edges the graphene, GRMs and their composite have also broad applications in electromagnetic shielding and electronic packaging [52]. Graphene-based touchscreen panels have also been designed [53]. Graphene and GRMs have also been explored for solar power generation owing to their optical transparency and high carrier mobility. In solar cells, graphene has been utilized as a buffer layer, electrode, and electron/hole transport medium material [54]. Sim et. al developed a graphene based CIGS solar cell in which graphene film was coated on the flexible copper foil through the CVD technique and used as a hole transport layer that yielded a power conversion efficiency of 9.91±0.89% [55].

Healthcare Applications: Microbial contamination is a big problem across the world that affects human health and in severe cases, it leads to the death of humans. The world has just witnessed one such infectious disease viz. COVID-19. Owing to their appealing properties, graphene and graphene-

related materials (GRMs) have shown potential to contribute to the fight against COVID-19 [56, 57]. Graphene and GRMs show antimicrobial and antiviral properties. Thus, graphene and GRMs can be used as fillers in polymeric materials or other biomaterials to boost their antimicrobial properties or can be applied as coatings on surfaces to prevent infection spread. Furthermore, graphene and GRMs display excellent electrical and surface properties. Moreover, their surfaces can be functionalized by various functional groups. These properties of graphene and GRMs make them promising candidates for high-performance biosensors too [58, 59]. The graphene-based biosensors have the potential for fast, precise, and highly sensitive diagnosis of viruses, various biomolecules, etc. A lot of work is underway on this subject across the world. Graphene stimuli responsive materials also snatch the attention of polymeric implants for on demand drug delivery [60]. According to reports, electroactive scaffolds retain their structural integrity while exhibiting regulated drug release in a pulsatile manner when modest electrical voltages are applied at low graphene concentrations (0.2 mg mL⁻¹) [61]. The most fascinating research GRMs on for regenerative medicine applications includes bone, nerve, cartilage, muscle, heart, skeletal, skin, and adipose tissue regeneration [62]. For example, the 3D graphene foams were developed and employed in bone regeneration. Crowder et al. fabricated 3D porous graphene foams by growing graphene on a 3D nickel scaffold and employed the 3D graphene foams as culture substrates for hMSCs [63]. Chen et al. developed graphene enhanced electronic skin (E-skin) for biomedical applications [64].

Tribological Applications: Tribology deals with friction, wear, and lubrication. t of contact sliding systems immensely suffer from high friction and wear. High friction, a force that renders the motion of the object, contributes to a huge amount of energy wastage [65]. A significant amount of energy in automobiles is used to combat friction. On

the other hand. wear is the damage/degradation the of components/systems. Manv commercial systems such as automobile components, turbines, MEMS/NEMS devices, nanoscale contact sliding devices, magnetic storage devices, engineering systems, etc., are hugely suffer from high friction and wear. Controlling/reducing friction and wear is essential for increasing the operational lifetime of the components, minimizing energy wastage, reducing economic loss, and saving the environment. Graphene has shown excellent tribological properties despite being just a single-atom-thick material [66]. It exceptionally reduces the friction of a wide variety of surfaces such as silicon, glass, ceramic, gold, mica, steel, etc., and considerably increases the wear resistance. Bilayer and few-layer graphene also show extraordinary tribological properties [66]. Thus, the application of graphene-based overcoats or graphene-reinforced composites can help to increase the operational lifetime of contact sliding components in various commercial systems [67].

Functional and soft robotic systems use graphene-based materials to increase the movement and response of sensors, actuators, and biomedical transplants [68-70]. In graphene composites, graphene addition also increases the thermal conductivity, which helps to increase the heat dissipation at the contact interfaces and reduces wear and deformation [68].

Sensors Applications: Graphene and GRMs are potential candidates for sensing applications. Graphene can attain a large strain without a considerable change in its electrical conductivity.

Thus, graphene-based high-performance strain sensors (in combination with other flexible polymers) can be designed and developed. The prototypes of graphene, GRMs, and graphene/GRMs-polymer composites-based flexible pressure sensors have already been demonstrated. The graphene, GRMs, and their composites-based sensors are crucial for healthcare applications such as in the development of blood pressure sensors. Kireev et. al developed a wearable, atomically thin, self-adhesive graphene electronic tattoo as a human bioelectronics interface for monitoring blood pressure based on electrical bio impedance [71]. Gao et.al developed a completely integrated sensor array for multiplexed in-situ perspiration analysis [72]. Kang et al. designed a graphene-based wearable thermal patch device that is used for thermotherapy and continuous skin temperature monitoring for self-care [73]. Graphene-based electrochemical sensors have also been developed to detect small biomolecules like uric acid, ascorbic acid, and dopamine in the human body [74, 75]. GRMs have also shown remarkable gas-sensing capability [76]. Graphene-based devices have been developed to detect toxic gases like SO_x, CO_x, and NO_x [77]. Moreover, Hu et.al used graphene-based plasmon devices for the detection of gas molecules such as SO₂, NO₂, N₂O₂, and NO [78].

Energy Storage: In contemporary society, there is a pressing demand to enhance the energy and power densities of electrochemical energy storage devices. Graphene has recently brought about significant advancements in portable electronics and electric vehicles by offering superior methods for electricity storage [79]. Battery and capacitors are important ways of storing energy; they follow the electrochemistry mechanism(s) to store the energy. However, there are always challenges that need to be solved for advanced technologies. The lithium-ion battery is commonly used as an energy storage device that uses a LiCoO₂ cathode and a graphite anode. The performance of the battery considerably depends on the properties of electrode materials. Since graphite anode has a low specific capacity (372 mAh g^{-1}), there is always a search for efficient anode material for Li-ion batteries. Graphene, rGO, and their composites with metal and metal oxides have been employed as anode material for Li-ion batteries. For example, Cu-supported graphene can reach specific capacities of 1500

mAh g⁻¹. Graphene and its hybrid with metal oxide are also proposed to be used as a current collector at the cathode. replacing conventional Al current collectors. There are many other components of Li-ion batteries where graphene and its composites with other materials can show promising properties and replace conventional materials. Furthermore, the combination of an aluminum anode with a cathode featuring high energy and power densities shapes the trajectory of aluminiumion battery technology [80]. The outlook for the Al-graphene pairing appears promising, provided immediate and focused efforts are directed toward overcoming the inherent technological challenges. While the concept of Aluminium-Ion Batteries (AIB) was initially conceived in the early 1970s, it gained significant attention in 2011 when the secondary nature of an Al-V2O5 cell at ambient temperature was demonstrated [81, 82]. The Al-graphene cell demonstrates the potential to provide an unexpectedly high power density (approximately 175 kW kg⁻¹), comparable to supercapacitors, while simultaneously maintaining an energy density (around 66 Wh kg⁻¹) higher than that of a leadacid battery [83]. Instances exist where combinations of energy and power densities reach 200 Wh kg⁻¹–200 W kg⁻¹ and 160 Wh kg⁻¹-50 kW kg⁻¹ [84]. Remarkably, the Algraphene cell achieves an exceptionally long lifespan, enduring up to a quarter-million cycles with minimal loss in specific capacity (approximately 111 mAh g⁻¹) when subjected to an immensely high current rate of 100 A g⁻¹ [85].

The supercapacitor is another important device for the giant storage of energy. A supercapacitor contains two electrodes and an electrolyte [86]. Unlike batteries, they function as energy storage devices that exhibit high power performance, featuring rapid charge and discharge times, minimal degradation over extended cycling periods, and environmental sustainability [87]. Nevertheless, these devices are unable to attain the elevated energy density achievable with batteries. Supercapacitors can be categorized into two types based on their

charge storage mechanisms: electric doublelayer capacitors (EDLCs) and well hvbrid pseudocapacitors, as as combinations thereof [88]. For the development of a good quality supercapacitor, the surface area of the materials must be as high as possible and the separation between the charges must be minimum. In particular, for electrodes, the materials should have high electrical conductivity and many other physicochemical excellent properties. Graphene, GRMs, and their composites have been explored for supercapacitor applications. Graphene has garnered considerable attention in the field of supercapacitors due to its exceptionally high surface area, reaching up to 2,630 m² g⁻¹ [89]. In the realm of energy storage, graphene emerges as a promising candidate for the next generation of supercapacitor electrodes owing to three primary factors. Firstly, its unrivaled surface area of 2630 m² g⁻¹ and remarkably low theoretical density of 2.28 g cm⁻³ grant the material a dual advantage of high packing density capability and an expansive specific surface area, facilitating efficient interaction with electrons and ions. Secondly, graphene exhibits exceptional electrical conductivity, featuring high motilities of up to 200,000 cm² V^{-1} S^{-1} at room temperature. This characteristic enables rapid electron and ion transfer across various device interfaces, such electrode/electrolyte as and electrode/collector. Additionally, the high electrical conductivity allows graphene to serve as both an active material and a current collector, eliminating the need for additional materials like binders and additives. Lastly, graphene demonstrates notable mechanical strength, boasting Young's modulus of 1 TPa and showcasing reversible strain up to 25%. This strength makes graphene suitable for applications flexible and printable in electronics while maintaining high capacitance retention [10. 89]. These graphene-based materials considerably change the electrode and electrolyte properties and suitably tailor the performance of supercapacitor. Graphene and GRMs have the high surface area and they are ultrathin both these properties make them potential candidates for electrode development. Owing to its large surface area and excellent conductivity, graphene was employed as an electrode for supercapacitors for the first time by Ruoff's research group [10]. Subsequently, efforts have been consistently directed towards strategies aimed at minimizing the agglomeration of graphene sheets to optimize both the accessible surface area and the development of extensive supercapacitors. Among the successful methodologies employed thus far is the utilization of graphene foam (GF) synthesized through chemical vapor deposition (CVD) [90-92]. Graphene exhibits a capacitance significantly lower than the theoretical capacitance values of 550 F g⁻¹ for supercapacitors and 744 mA h g^{-1} for lithium-ion batteries [93]. The charge storage mechanism observed in pristine graphene supercapacitor materials falls under electrical double-layer capacitance (EDLC), wherein the charge is physically stored through the adsorption of electrolyte ions onto the graphene surface [94]. When the entire specific surface area (SSA) of 2630 m² g⁻¹ is fully utilized, graphene electrode materials exhibit an electrical double-layer can capacitance (EDLC) of 550 F g⁻¹. further to this capacitance doped enhance and functionalized graphene, and graphene have been engineered composites to incorporate extra pseudocapacitance [95, 96]. Achieving the theoretical charge storage limit electrode materials of graphene for application in electrochemical energy storage devices demands extensive efforts in the systematic design of the structure and chemistry of graphene materials.

Water desalination: Graphene demonstrates high impermeability against contaminants and allows the water to pass through it. This property of graphene and GRMs enables them to be promising candidates for water purification applications [97]. Graphene and GRMs are used not only for drinking water desalination but also effective in the purification of the sea and industrial waste water[98, 99]. Water desalination requires effective ion sieving as well as ultra-fast water flow for continuous supply, in which graphene and GRMs possess an extensive advantage through nanofiltration membranes with sub-nano to atomic-scale capillaries (6 Å)[100, 101]. Graphene and graphene possess antimicrobial properties that improve water purification quality [102]. Moreover, various molecules and methods are utilized to control and modify the graphene and GRM pour size for selective ion sieving. For example, Chung et al modified GRMs (GO)with ethylenediamine, which was used for the separation of Pb²⁺, Ni²⁺, Cd²⁺, and Zn²⁺ with obtained maximum rejection up to 95.7, 96.0, 90.5, and 97.4%, respectively and attained the water permeability of ~5.0 L m⁻² h⁻¹ bar⁻¹ [103], Gong et.al confined the GRMs (GO) interlamination to 0.71nm with 99.9% restriction of organic ion NaCl. [104] Likewise, Chen et. al demonstrated a scalable production of subnanometer porous ultrathin graphene membrane by subsequent reduction and carbonization of the GO nanosheets and polymer on the ceramic porous substrate; they achieved a water evaporation flux of $49.8 \pm 1.5 {-}472.3 \pm 14.2 \ L\ m^{-2}\ h^{-1}$ and

99.99% NaCl rejection at 20-70 °C [105]. Salt dve separation from water is also a big concern, Padmavathy et. al exploited a GRMs-based system for various dve separation and divalent ion rejection [106]. Although, the graphene and GRMs-related framework performs better in water desalination their commercialization and scalability are the most critical aspect, along with the large quantity and high quality production of graphene.

Graphene-composites: Composites of graphene with metals and polymers display enhanced properties due to the application of graphene. The introduction of graphene and GRMs improves various properties of metals and polymers such as electrical properties (increase the electrical conductivity) [107], thermal properties (increase the thermal conductivity) [108], mechanical properties (increase the mechanical strength) [109], tribological properties (reduce the friction and wear) [110], corrosion property (reduce the

corrosion) [111], shielding properties (enhance the electromagnetic shielding) [112], and so on. Thus, graphene-metal and graphene-polymer composites are promising candidates for many commercial applications. GRMs are majorly investigated in most graphene-polymer composites considering their low cost and high yield production. GO enhances the mechanical and thermal properties of hydrophilic polymers like POP [113] and PVA[114]. Considerable work has been carried out on amination[115], esterification [116], isocyanate modification[117], and polymer grafting [118] for the functionalization of GO by forming chemical bonds with the carboxyl and hydroxyl groups to enhance the applications of GO [119]. As polymers are mostly electrically insulating, reduced GO can significantly increase its electrical conductivity [120], but agglomeration or restacking causes difficulty in composite fabrication. CVD graphene as a filler offers various π interactions (C- π , π – π , π –H, etc.) because of plenty of π electrons on the CVD graphene that results in the ample amount of interfacial interaction with polymer matrix [121]. Yan et.al successfully synthesized aligned graphene nanowalls vertically (GNWs) which were covalently bonded by high-quality CVD graphene nanosheets; this filler yielded high thermal conductivity (12.8 \pm 0.77 W m⁻¹ K⁻¹) of polyvinylidene fluoride (PVDF) at a low filler content of 4.0 wt.% [122].

Acknowledgments: The authors wish to thank the Director, CSIR-AMPRI, for his kind support. The authors also wish to thank Scientists of CSIR-AMPRI for providing their input on graphene related literature.

Nature.

References:

- [1] Geim AK, Kim P. CARBON WONDERLAND. Scientific American. 2008;298(4):90-7.
- [2] Das RR, Reghuvaran C, James A. Graphene-based RRAM devices for neural computing. Frontiers in Neuroscience. 2023;17.
- [3] Chuvilin A, Kaiser U, Bichoutskaia E, Besley NA, Khlobystov AN. Direct transformation of graphene to fullerene. Nature Chemistry. 2010;2(6):450-3.
- [4] Bacon M, Bradley SJ, Nann T. Graphene Quantum Dots. Particle & Particle Systems Characterization. 2014;31(4):415-28.
- [5] Marinho B, Ghislandi M, Tkalya E, Koning CE, de With G. Electrical conductivity of compacts of graphene, multi-wall carbon nanotubes, carbon black, and graphite powder. Powder Technology. 2012;221:351-8.
- [6] Papageorgiou DG, Kinloch IA, Young RJ. Mechanical properties of graphene and graphene-based nanocomposites. Progress in Materials Science. 2017;90:75-127.
- [7] Bonaccorso F, Colombo L, Yu G, Stoller M, Tozzini V, Ferrari AC, et al. Graphene, related two-dimensional crystals, and hybrid systems for energy conversion and storage. Science. 2015;347(6217).
- [8] Kuzmenko A, Van Heumen E, Carbone F, Van Der Marel D. Universal optical conductance of graphite. Physical review letters. 2008;100(11):117401.
- [9] Huang X, Yin Z, Wu S, Qi X, He Q, Zhang Q, et al. Graphene-Based Materials: Synthesis, Characterization, Properties, and Applications. Small. 2011;7(14):1876-902.
- [10] Stoller MD, Park S, Zhu Y, An J, Ruoff RS. Graphene-Based Ultracapacitors. Nano Letters. 2008;8(10):3498-502.
- [11] Kosynkin DV, Higginbotham AL, Sinitskii A, Lomeda JR, Dimiev A, Price BK, et al. Longitudinal unzipping of carbon nanotubes to form graphene

nanoribbons. 2009;458(7240):872-6.

- [12] Novoselov KS, Geim AK, Morozov SV, Jiang D, Zhang Y, Dubonos SV, et al. Electric field effect in atomically thin carbon films. Science. 2004;306(5696):666-9.
- [13] Yan Y, Nashath FZ, Chen S, Manickam S, Lim SS, Zhao H, et al. Synthesis of graphene: Potential carbon precursors and approaches. 2020;9(1):1284-314.
- [14] Hass J, De Heer W, Conrad E. The growth and morphology of epitaxial multilayer graphene. Journal of Physics: Condensed Matter. 2008;20(32):323202.
- [15] Norimatsu W. A Review on Carrier Mobilities of Epitaxial Graphene on Silicon Carbide. Materials2023.
- [16] Zhan N, Olmedo M, Wang G, Liu J. Layer-by-layer synthesis of large-area graphene films by thermal cracker enhanced gas source molecular beam epitaxy. Carbon. 2011;49(6):2046-52.
- [17] Bharti DK, Gupta MK, Kumar R, Sathish N, Srivastava AK. Noncentrosymmetric zinc silicate-graphene based transparent flexible piezoelectric nanogenerator. Nano Energy. 2020:104821.
- [18] Li X, Cai W, An J, Kim S, Nah J, Yang D, et al. Large-Area Synthesis of High-Quality and Uniform Graphene Films on Copper Foils. Science. 2009;324(5932):1312-4.
- [19] Reina A, Jia X, Ho J, Nezich D, Son H, Bulovic V, et al. Large Area, Few-Layer Graphene Films on Arbitrary Substrates by Chemical Vapor Deposition. Nano Letters. 2009;9(1):30-5.
- [20] MOOSA A, ABED M. Graphene preparation and graphite exfoliation. Turkish journal of Chemistry. 2021;45(3):493-519.
- [21] Brodie BC. XIII. On the atomic weight of graphite. Philosophical Transactions of the Royal Society of London. 1997;149:249-59.
- [22] Staudenmaier L. Verfahren zur Darstellung der Graphitsäure. Berichte

der deutschen chemischen Gesellschaft. 1899;32(2):1394-9.

- [23] Agrawal PR, Kumar R, Teotia S, Kumari S, Mondal DP, Dhakate SR. Lightweight, high electrical and thermal conducting carbon-rGO composites foam for superior electromagnetic interference shielding. Composites Part B: Engineering. 2019;160:131-9.
- [24] Marcano DC, Kosynkin DV, Berlin JM, Sinitskii A, Sun Z, Slesarev A, et al. Improved Synthesis of Graphene Oxide. ACS Nano. 2010;4(8):4806-14.
- [25] Kumar N, Salehiyan R, Chauke V, Joseph Botlhoko O, Setshedi K, Scriba M, et al. Top-down synthesis of graphene: A comprehensive review. FlatChem. 2021;27:100224.
- [26] Abtew MA, Boussu F, Bruniaux P. Dynamic impact protective body armour: A comprehensive appraisal on panel engineering design and its prospective materials. Defence Technology. 2021;17(6):2027-49.
- [27] Mueller T, Xia F, Avouris P. Graphene photodetectors for high-speed optical communications. Nature Photonics. 2010;4(5):297-301.
- [28] Jung HS, Lee M-Y, Kong WH, Do IH, Hahn SK. Nano graphene oxide– hyaluronic acid conjugate for target specific cancer drug delivery. RSC Advances. 2014;4(27):14197-200.
- [29] Yu H, Liu X, Zheng Z, Qiao D, Feng D, Gong Z, et al. In Situ Graphene Formation Induced by Tribochemical Reaction for Sustainable Lubrication. ACS Sustainable Chemistry & Engineering. 2023;11(6):2238-48.
- [30] Guy R. Managing diabetes through the skin. Nature Nanotechnology. 2016;11(6):493-4.
- [31] Jose J, Jose SP, Prasankumar T, Shaji S, Pillai S, B SP. Emerging ternary nanocomposite of rGO draped palladium oxide/polypyrrole for high performance supercapacitors. Journal of Alloys and Compounds. 2021;855:157481.

- [32] Song Z, Niu Y, Yang J, Chen L, Chen J. Comparison of water desalination performance of porous graphene and MoS2 nanosheets. RSC Advances. 2022;12(42):27641-7.
- [33] Kausar A, Ahmad I, Eisa MH, Maaza M. Graphene Nanocomposites in Space Sector—Fundamentals and Advancements. C2023.
- [34] Gong L, Young RJ, Kinloch IA, Riaz I, Jalil R, Novoselov KS. Optimizing the Reinforcement of Polymer-Based Nanocomposites by Graphene. ACS Nano. 2012;6(3):2086-95.
- [35] Kim Y, Lee J, Yeom MS, Shin JW, Kim H, Cui Y, et al. Strengthening effect of single-atomic-layer graphene in metal– graphene nanolayered composites. Nature Communications. 2013;4(1):2114.
- [36] Kim J, Kim J, Song S, Zhang S, Cha J, Kim K, et al. Strength dependence of epoxy composites on the average filler size of non-oxidized graphene flake. Carbon. 2017;113:379-86.
- [37] Krystek M, Pakulski D, Patroniak V, Górski M, Szojda L, Ciesielski A, et al. High-Performance Graphene-Based Cementitious Composites. Advanced Science. 2019;6(9):1801195.
- [38] Huang C, Peng J, Cheng Y, Zhao Q, Du Y, Dou S, et al. Ultratough nacreinspired epoxy–graphene composites with shape memory properties. Journal of Materials Chemistry A. 2019;7(6):2787-94.
- [39] Abolhasani D, Moon B, Kang N, VanTyne CJ, Moon YH. Highperformance Cu-Al shape memory alloy in ternary combination with graphene fabricated by powder bed fusion process. Journal of Alloys and Compounds. 2023;960:170707.
- [40] Krishnamoorthy K, Pazhamalai P, Mariappan VK, Manoharan S, Kesavan **Two-Dimensional** D, Kim S-J. Siloxene–Graphene Heterostructure-Based **High-Performance** Supercapacitor for Capturing Regenerative Braking Energy in

Electric Vehicles. Advanced Functional Materials. 2021;31(10):2008422.

- [41] Li L, Sun T, Lu S, Chen Z, Xu S, Jian M, et al. Graphene Interlocking Carbon Nanotubes for High-Strength and High-Conductivity Fibers. ACS Applied Materials & Interfaces. 2023;15(4):5701-8.
- [42] Pasricha R, Gupta S, Srivastava AK. A facile and novel synthesis of Ag-graphene-based nanocomposites. Small. 2009;5(20):2253-9.
- [43] Xia F, Mueller T, Lin Y-m, Valdes-Garcia A, Avouris P. Ultrafast graphene photodetector. Nature Nanotechnology. 2009;4(12):839-43.
- [44] Liu M, Yin X, Ulin-Avila E, Geng B, Zentgraf T, Ju L, et al. A graphenebased broadband optical modulator. Nature. 2011;474(7349):64-7.
- [45] Echtermeyer TJ, Britnell L, Jasnos PK, Lombardo A, Gorbachev RV, Grigorenko AN, et al. Strong plasmonic enhancement of photovoltage in graphene. Nature Communications. 2011;2(1):458.
- [46] Sun Z, Hasan T, Torrisi F, Popa D, Privitera G, Wang F, et al. Graphene Mode-Locked Ultrafast Laser. ACS Nano. 2010;4(2):803-10.
- [47] Saraswat V, Jacobberger RM, Arnold MS. Materials Science Challenges to Graphene Nanoribbon Electronics. ACS Nano. 2021;15(3):3674-708.
- [48] Miao J, Fan T. Flexible and stretchable transparent conductive graphene-based electrodes for emerging wearable electronics. Carbon. 2023;202:495-527.
- [49] Vicarelli L, Vitiello MS, Coquillat D, Lombardo A, Ferrari AC, Knap W, et al. Graphene field-effect transistors as room-temperature terahertz detectors. Nature Materials. 2012;11(10):865-71.
- [50] Simionescu O-G, Avram A, Adiaconiță
 B, Preda P, Pârvulescu C, Năstase F, et al. Field-Effect Transistors Based on Single-Layer Graphene and Graphene-Derived Materials. Micromachines2023.

- [51] Ciou S-H, Hsieh A-H, Lin Y-X, Sei J-L, Govindasamy M, Kuo C-F, et al. Sensitive label-free detection of the biomarker phosphorylated tau-217 protein in Alzheimer's disease using a graphene-based solution-gated field effect transistor. Biosensors and Bioelectronics. 2023;228:115174.
- [52] Lai D, Chen Z, Han Z, Wu Z-S, Chen X. Progress and roadmap for graphene films in electromagnetic interference shielding. Resources Chemicals and Materials. 2023;2(1):11-38.
- [53] Dong X, Long Q, Wei A, Zhang W, Li L-J, Chen P, et al. The electrical properties of graphene modified by bromophenyl groups derived from a diazonium compound. Carbon. 2012;50(4):1517-22.
- [54] Mahmoudi T, Wang Y, Hahn Y-B. Graphene and its derivatives for solar cells application. Nano Energy. 2018;47:51-65.
- [55] Sim J-K, Kang S, Nandi R, Jo J-Y, Jeong K-U, Lee C-R. Implementation of graphene as hole transport electrode in flexible CIGS solar cells fabricated on Cu foil. Solar Energy. 2018;162:357-63.
- [56] Srivastava A, Dwivedi N, Dhand C, Khan R, Sathish N. Can Graphene-based Materials Play a Role in the Fight against COVID-19? 2020.
- [57] Sharma A, Kumar R, Patle VK, Dhawan R, Abhash A, Dwivedi N, et al. Phenol formaldehyde resin derived carbon-MCMB composite foams for electromagnetic interference shielding and thermal management applications. Composites Communications. 2020;22:100433.
- [58] Jiang Z, Feng B, Xu J, Qing T, Zhang P, Qing Z. Graphene biosensors for bacterial and viral pathogens. Biosensors and Bioelectronics. 2020;166:112471.
- [59] Fahmy HM, Abu Serea ES, Salah-Eldin RE, Al-Hafiry SA, Ali MK, Shalan AE, et al. Recent Progress in Graphene- and Related Carbon-Nanomaterial-based

Electrochemical Biosensors for Early Disease Detection. ACS Biomaterials Science & Engineering. 2022;8(3):964-1000.

- [60] Brindhadevi K, Garalleh HAL, Alalawi A, Al-Sarayreh E, Pugazhendhi A. Carbon nanomaterials: Types, synthesis strategies and their application as drug delivery system for cancer therapy. Biochemical Engineering Journal. 2023;192:108828.
- [61] Servant A, Leon V, Jasim D, Methven L, Limousin P, Fernandez-Pacheco EV, et al. Graphene-Based Electroresponsive Scaffolds as Polymeric Implants for On-Demand Drug Delivery. Advanced Healthcare Materials. 2014;3(8):1334-43.
- [62] Ding X, Liu H, Fan Y. Graphene-Based Materials in Regenerative Medicine. Advanced Healthcare Materials. 2015;4(10):1451-68.
- [63] Crowder SW, Prasai D, Rath R, Balikov DA, Bae H, Bolotin KI, et al. Threedimensional graphene foams promote osteogenic differentiation of human mesenchymal stem cells. Nanoscale. 2013;5(10):4171-6.
- [64] Chen X, Luo F, Yuan M, Xie D, Shen L,
 Zheng K, et al. A Dual-Functional
 Graphene-Based Self-Alarm HealthMonitoring E-Skin. Advanced
 Functional Materials.
 2019;29(51):1904706.
- [65] Dwivedi N, Yeo RJ, Dhand C, Risan J, Nay R, Tripathy S, et al. Boosting contact sliding and wear protection via atomic intermixing and tailoring of nanoscale interfaces. Science Advances.5(1):eaau7886.
- [66] Bharti P, Sunkara SV, Vishwakarma J, Jaiswal S, Dhand C, Kumar R, et al. Simultaneous Control of Sliding Contact and Oxidation via Graphene-Based Materials. ACS Applied Engineering Materials. 2023;1(8):2062-74.
- [67] Dwivedi N, Patra T, Lee J-B, Yeo RJ, Srinivasan S, Dutta T, et al. Slippery and Wear-Resistant Surfaces Enabled

by Interface Engineered Graphene. Nano Letters. 2020;20(2):905-17.

- [68] Bai M-j, Liu J-l, He J, Li W-j, Wei J-j, Chen L-x, et al. Heat transfer and mechanical friction reduction properties of graphene oxide nanofluids. Diamond and Related Materials. 2020;108:107982.
- [69] Trucco D, Vannozzi L, Teblum E, Telkhozhayeva M, Nessim GD, Affatato S, et al. Graphene Oxide-Doped Gellan Gum–PEGDA Bilayered Hydrogel Mimicking the Mechanical and Lubrication Properties of Articular Cartilage. Advanced Healthcare Materials. 2021;10(7):2001434.
- [70] Vishwakarma J, Jaiswal S, Bharti P, Dhand C, Kumar R, Hashmi SAR, et al. Competing and decisive roles of 1D/2D/3D sp2-carbons in controlling the shape switching, contact sliding, and functional properties of polymers. Materials Today Chemistry. 2022;25:100960.
- [71] Kireev D, Sel K, Ibrahim B, Kumar N, Akbari A, Jafari R, et al. Continuous cuffless monitoring of arterial blood pressure via graphene bioimpedance tattoos. Nature Nanotechnology. 2022;17(8):864-70.
- [72] Gao W, Emaminejad S, Nyein HYY, Challa S, Chen K, Peck A, et al. Fully integrated wearable sensor arrays for multiplexed in situ perspiration analysis. Nature. 2016;529(7587):509-14.
- [73] Kang M, Jeong H, Park S-W, Hong J, Lee
 H, Chae Y, et al. Wireless graphenebased thermal patch for obtaining temperature distribution and performing thermography. Science Advances.8(15):eabm6693.
- [74] Sheng Z-H, Zheng X-Q, Xu J-Y, Bao W-J, Wang F-B, Xia X-H. Electrochemical sensor based on nitrogen doped graphene: Simultaneous determination of ascorbic acid, dopamine and uric acid. Biosensors and Bioelectronics. 2012;34(1):125-31.

- [75] Matsumoto K, Maehashi K, Ohno Y, Inoue K. Recent advances in functional graphene biosensors. Journal of Physics D: Applied Physics. 2014;47(9):094005.
- [76] Lu G, Ocola LE, Chen J. Reduced graphene oxide for room-temperature gas sensors. Nanotechnology. 2009;20(44):445502.
- [77] Cruz-Martínez H, Rojas-Chávez H, Montejo-Alvaro F, Peña-Castañeda YA, Matadamas-Ortiz PT, Medina DI. Recent Developments in Graphene-Based Toxic Gas Sensors: A Theoretical Overview. Sensors2021.
- [78] Hu H, Yang X, Guo X, Khaliji K, Biswas SR, García de Abajo FJ, et al. Gas identification with graphene plasmons. Nature Communications. 2019;10(1):1131.
- [79] El-Kady MF, Shao Y, Kaner RB. Graphene for batteries, supercapacitors and beyond. Nature Reviews Materials. 2016;1:16033.
- [80] Das SK. Graphene: A Cathode Material of Choice for Aluminum-Ion Batteries. Angewandte Chemie International Edition. 2018;57(51):16606-17.
- [81] Holleck GL. The Reduction of Chlorine on Carbon in AlCl3 - KCl - NaCl Melts. Journal of The Electrochemical Society. 1972;119(9):1158.
- [82] Jayaprakash N, Das SK, Archer LA. The rechargeable aluminum-ion battery. Chemical Communications. 2011;47(47):12610-2.
- [83] Chen H, Xu H, Wang S, Huang T, Xi J, Cai S, et al. Ultrafast all-climate aluminum-graphene battery with quarter-million cycle life. Science Advances.3(12):eaao7233.
- [84] Liu C, Liu Z, Niu H, Wang C, Wang Z, Gao B, et al. Preparation and in-situ Raman characterization of binder-free u-GF@CFC cathode for rechargeable aluminum-ion battery. MethodsX. 2019;6:2374-83.
- [85] Simon P, Gogotsi Y, Dunn B. Where Do Batteries End and Supercapacitors

Begin? Science. 2014;343(6176):1210-1.

- [86] Ahmad F, Zahid M, Jamil H, Khan M, Atiq S, Bibi M, et al. Advances in graphene-based electrode materials for high-performance supercapacitors: A review. Journal of Energy Storage. 2023;Volume 72, Part E:108731.
- [87] Velasco A, Ryu YK, Boscá A, Ladrónde-Guevara A, Hunt E, Zuo J, et al. Recent trends in graphene supercapacitors: from large area to microsupercapacitors. Sustainable Energy & Fuels. 2021;5(5):1235-54.
- [88] Borenstein A, Hanna O, Attias R, Luski S, Brousse T, Aurbach D. Carbon-based composite materials for supercapacitor electrodes: a review. Journal of Materials Chemistry A. 2017;5(25):12653-72.
- [89] El-Kady M, Shao Y, Kaner R. Graphene for batteries, supercapacitors and beyond. Nature Reviews Materials. 2016;1:16033.
- [90] Chen Z, Ren W, Gao L, Liu B, Pei S, Cheng H-M. Three-dimensional flexible and conductive interconnected graphene networks grown by chemical vapour deposition. Nature Materials. 2011;10(6):424-8.
- [91] Tiwari S, Sahoo S, Wang N, Huczko A. Graphene Research and their Outputs: Status and Prospect. Journal of Science: Advanced Materials and Devices. 2020;5.
- [92] Randviir EP, Brownson DAC, Banks CE. A decade of graphene research: production, applications and outlook. Materials Today. 2014;17(9):426-32.
- [93] Chen K, Song S, Liu F, Xue D. Structural design of graphene for use in electrochemical energy storage devices. Chemical Society Reviews. 2015;44(17):6230-57.
- [94] Raccichini R, Varzi A, Passerini S, Scrosati B. The role of graphene for electrochemical energy storage. Nature Materials. 2015;14(3):271-9.
- [95] Xia J, Chen F, Li J, Tao N. Measurement of the quantum capacitance of graphene.

Nature Nanotechnology. 2009;4(8):505-9.

- [96] Ambrosi A, Chua CK, Bonanni A, Pumera M. Electrochemistry of Graphene and Related Materials. Chemical Reviews. 2014;114(14):7150-88.
- [97] Gkika DA, Karmali V, Lambropoulou DA, Mitropoulos AC, Kyzas GZ. Membranes Coated with Graphene-Based Materials: A Review. Membranes2023.
- [98] Homaeigohar S, Elbahri M. Graphene membranes for water desalination. NPG Asia Materials. 2017;9(8):e427-e.
- [99] Castro-Muñoz R. A critical review on electrospun membranes containing 2D materials for seawater desalination. Desalination. 2023;555:116528.
- [100] Zhang Q, Gao B, Zhang L, Liu X, Cui J, Cao Y, et al. Anomalous water molecular gating from atomic-scale graphene capillaries for precise and ultrafast molecular sieving. Nature Communications. 2023;14(1):6615.
- [101] Radha B, Esfandiar A, Wang FC, Rooney AP, Gopinadhan K, Keerthi A, et al. Molecular transport through capillaries made with atomic-scale precision. Nature. 2016;538(7624):222-5.
- [102] Mahmoud KA, Mansoor B, Mansour A, Khraisheh M. Functional graphene nanosheets: The next generation membranes for water desalination. Desalination. 2015;356:208-25.
- [103] Zhang Y, Zhang S, Chung T-S. Nanometric Graphene Oxide Framework Membranes with Enhanced Heavy Metal Removal via Nanofiltration. Environmental Science & Technology. 2015;49(16):10235-42.
- [104] Gong D, Liu X, Wu P, Wang Y, Guo B, Liu S, et al. Water pumping effect over the organic ions defined graphene oxide membrane impulses high flux desalination. npj Clean Water. 2022;5(1):68.
- [105] Chen X, Zhu Y-B, Yu H, Liu JZ, Easton CD, Wang Z, et al. Ultrafast water

evaporation through graphene membranes with subnanometer pores for desalination. Journal of Membrane Science. 2021;621:118934.

- [106] Padmavathy N, Behera SS, Pathan S, Das Ghosh L, Bose S. Interlocked Graphene Oxide Provides Narrow Channels for Effective Water Desalination through Forward Osmosis. ACS Applied Materials & Interfaces. 2019;11(7):7566-75.
- [107] Cai X, Sun K, Qiu Y, Jiao X. Recent Advances in Graphene and Conductive Polymer Composites for Supercapacitor Electrodes: A Review. Crystals2021.
- [108] Huang X, Zhi C, Lin Y, Bao H, Wu G, Jiang P, et al. Thermal conductivity of graphene-based polymer nanocomposites. Materials Science and Engineering: R: Reports. 2020;142:100577.
- [109] Lodhi RS, Kumar P, Achuthanunni A, Rahaman M, Das P. 3 - Mechanical properties of polymer/graphene composites. In: Rahaman M, Nayak L, Hussein IA, Das NC, editors. Polymer Nanocomposites Containing Graphene: Woodhead Publishing; 2022. p. 75-105.
- [110] Sarath PS, Reghunath R, Thomas S, Haponiuk JT, George SC. 8 - Tribology of graphene-based polymeric systems. In: George SC, Haponiuk JT, Thomas S, Reghunath R, P. S S, editors. Tribology of Polymers, Polymer Composites, and Polymer Nanocomposites: Elsevier; 2023. p. 215-33.
- [111] Sharma A, Sharma S. Graphene-based polymer coatings for preventing marine corrosion: a review. JOURNAL OF COATINGS TECHNOLOGY AND RESEARCH. 2023;20(2):413-32.
- [112] Kausar A, Ahmad I, Zhao T, Aldaghri O, Ibnaouf KH, Eisa MH, et al. Graphene Nanocomposites for Electromagnetic Interference Shielding—Trends and Advancements. Journal of Composites Science2023.
- [113] Liu H, Yang W, He F, Li Y, Yang X, Zhang K. Graphene-based composite

with microwave absorption property prepared by in situ reduction. Polymer Composites. 2014;35(3):461-7.

- [114] Morimune S, Nishino T, Goto T. Poly(vinyl alcohol)/graphene oxide nanocomposites prepared by a simple eco-process. Polymer Journal. 2012;44(10):1056-63.
- [115] Wang J-Y, Yang S-Y, Huang Y-L, Tien H-W, Chin W-K, Ma C-CM. Preparation and properties of graphene oxide/polyimide composite films with low dielectric constant and ultrahigh strength via in situpolymerization. Journal of Materials Chemistry. 2011;21(35):13569-75.
- [116] Pham TA, Kumar NA, Jeong YT. Covalent functionalization of graphene oxide with polyglycerol and their use as templates for anchoring magnetic nanoparticles. Synthetic Metals. 2010;160(17):2028-36.
- [117] Stankovich S, Dikin DA, Dommett GHB, Kohlhaas KM, Zimney EJ, Stach EA, et al. Graphene-based composite materials. Nature. 2006;442(7100):282-6.
- [118] Gonçalves G, Marques PAAP, Barros-Timmons A, Bdkin I, Singh MK, Emami N, et al. Graphene oxide modified with PMMA via ATRP as a reinforcement filler. Journal of Materials Chemistry. 2010;20(44):9927-34.
- [119] Kuilla T, Bhadra S, Yao D, Kim NH, Bose S, Lee JH. Recent advances in graphene based polymer composites. Progress in Polymer Science. 2010;35(11):1350-75.
- [120] Li M, Gao C, Hu H, Zhao Z. Electrical conductivity of thermally reduced graphene oxide/polymer composites with a segregated structure. Carbon. 2013;65:371-3.
- [121] Xiao X, Xie T, Cheng Y-T. Selfhealable graphene polymer composites. Journal of Materials Chemistry. 2010;20(17):3508-14.
- [122] Yan Q, Gao J, Chen D, Tao P, Chen L, Ying J, et al. A highly orientational

architecture formed by covalently bonded graphene to achieve high through-plane thermal conductivity of polymer composites. Nanoscale. 2022;14(31):11171-8.